



## AL665\_V

### Fade Out Thinner - Aerosol

<b>Description</b>	<b>AUTOLUX® Fade Out Thinner, AL665</b> , offers an easy and simple fade-out process to cover all types of work. It is formulated for easy application and has excellent overspray wetting properties, giving a high gloss and quality finish to the fade-out process.
<b>Products</b>	AL665 <i>Autolux</i> Fade-Out Thinner
<b>Surface Preparation</b>	<ol style="list-style-type: none"> <li>1. Ensure that all panels that may be involved in the repair or fade-out are thoroughly clean (refer to TDS for <i>Autolux</i> Multi Purpose Cleaner, AL641 and <i>Autolux</i> Panel Wipe, AL644).</li> <li>2. Flat the repaired and primed area, with no coarser than P800 for wet flattening or P400 for dry machine sanding.</li> <li>3. Prepare surrounding area using a Water-based Flattening Paste with an abrasive Scotch-Brite Grey Ultrafine pad. Clean with suitable pre-cleaner Tak rag off before spraying.</li> </ol>
<b>Mixing</b> 	Supplied ready to use  Shake aerosol for at least 1 minute before use
<b>Application</b> 	After normal application the gun is arced away from the panel in the fade-out area leaving a dry overspray blend.  Apply <i>Autolux</i> Fade Out Thinner to the Clearcoat edge, applying in light coats to melt the overspray edge. <b>DO NOT</b> apply heavily.  Allow the paint film to cure.  Polish the fade-out area with a polishing compound, taking care not to polish through the blend, and finish with a finishing polish.  Spraying Distance: 20 – 30 cm.
<b>VOC Information</b>  The EU limit value for this product (product category: IIB.e) in ready to use form is max. 840g/litre of VOC. The VOC content of this product in ready to use form is max. 840g/litre. Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.	

**These products are for professional painting only**, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the Material Safety Data Sheet. March 2014.

AUTOLUX® & the AUTOLUX® logo are trademarks of PPG Industries Ohio, Inc. © 2014 PPG Industries. All rights reserved.

PPG Industries (UK) Ltd, Auto Refinish Customer Service & Sales Group, Needham Road, Stowmarket, Suffolk IP14 2AD, Tel: 01449 771775