









**AL787\_V**  
**Soft Stopper**

<b>Description</b>	<b>AUTOLUX® Soft Stopper, AL787</b> , is a highly flexible, polyester based stopper which easy to apply and sand.		
<b>Products</b>	Stopper: Hardener:	AL787 <i>Autolux</i> Soft Stopper SHA305 <i>Autolux</i> Hardener for AL787	
<b>Substrates</b>	Bare metal: steel, galvanized steel and aluminium SMC and FRP Old finishes in sound condition		
<b>Surface Preparation</b>		Bare metal: Scuff well Old finishes: Machine sand P80-P180 grit	 Degrease the surface thoroughly before and after sanding. Before application the surface must be completely dry.
<b>Mixing</b>		<i>Autolux</i> Soft Stopper AL787 <i>Autolux</i> Hardener SHA305	By weight: 100 Parts 2 - 3 Parts
<b>Working Time:</b> 4 - 6 min, depending on temperature and proportion of hardener.			
<b>Application</b>		Use a suitable knife or spreader.	
<b>Drying</b>		Stopper dry to sand on 20 – 30 min. at 20°C.  I.R - Short Wave            2 – 3 minutes* - Medium Wave        5 – 7 minutes*  *Depending on IR equipment used	
<b>Sanding</b>	 	Dry: P80–P120, to desired contour.  Finishing P180–P240	
<b>Recoat</b>		Stopper can be recoated with <i>Autolux</i> CFE Primer, Epoxy Primer or 2K Primer Surfacer	
<b>Process Notes</b> Clean up equipment immediately after use, using <i>Autolux</i> Thinner or another suitable solvent. Dispose of waste in accordance with applicable regulations.			
<b>VOC Information</b> The EU limit value for this product (product category: IIB.b) in ready to use form is max. 250g/litre of VOC. The VOC content of this product in ready to use form is max. 250g/litre. Depending on the chosen mode of use, the actual ready to use VOC of this product may be lower than that specified by the EU Directive code.			

**These products are for professional painting only**, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the Material Safety Data Sheet. March 2014.

AUTOLUX® & the AUTOLUX® logo are trademarks of PPG Industries Ohio, Inc. © 2014 PPG Industries. All rights reserved.

PPG Industries (UK) Ltd, Auto Refinish Customer Service & Sales Group, Needham Road, Stowmarket, Suffolk IP14 2AD, Tel: 01449 771775